

PREMIUM NON-DRIP INTERIOR

SATIN ENAMEL



CODE:

DSE

Description:

Thixotropic, semi-gloss Polyurethane enamel.

Product Benefits:

Dries to an extremely hardwearing semi-sheen finish.
Scrubable - suitable for high traffic areas where constant cleaning is required.
The thixotropic nature of the product provides for good flow properties which will not show brush marks.
Resistant to mould growth. Ideal for kitchens and bathrooms.

SURFACE PREPARATION:

New Work:

1. Concrete and plaster surfaces must be primed with Alkali Resistant Primer.
2. Wooden surfaces must be primed with Wood Primer and Universal undercoat.
3. Metal surfaces must be primed with RP4, excluding very smooth surfaces e.g. New Mild steel, galvanising or aluminium which must be coated with Vinyl Wash Primer I Acid Etch Primer and Universal Undercoat.

Previously Painted Surfaces:

1. Surfaces must be in sound condition.
2. Loose and flaking paint must be removed.
3. Old enamel or oil paints must be sanded and suitably primed.
4. Chalky surfaces must be well brushed and sealed with Alkali Resistant Primer.

General:

1. All substrates should be clean, dry, sound and free of grease and oils before painting.
2. Hairline cracks, imperfections should be filled with a suitable Masonry Crack Filler, and primed with Masonry Primer, before application of the paint system.
3. Consult our sales staff for application onto any other substrate.
4. Not compatible with pliolite based products e.g. Masonry Primer.

APPLICATION:

Ready to use. Brush or mohair application.
Apply 2 coats sanding lightly between coats.
Clean with mineral Turpentine. Once agitated or stirred, the product must be left for 3 hours for gel recovery.

TECHNICAL DATA:

SG:	1.25 +/- 0.05
Viscosity:	90 - 100 KU
Drying Time: (T)	4 hours
@ 25°C: (H)	24 hours
Overcoating:	16 hours
Solid Mass:	58 - 60%
Gloss @ 60°:	20 - 30% Sheen
Spread Rate:	7 - 8m ² / Lt
Colour Range	White
Bases:	Pastel, Deep, Transparent

Note: Certain transparent colours may require a minimum of 3 coats to achieve total obliteration.