

# TRADE ROOF PAINT

**CODE:****DTR****DESCRIPTION:**

Trade Roof Paint is an economical, versatile quick drying water based Pure Acrylic Paint providing excellent adhesion to fibre cement, cement roof tiles, galvanised iron and zinc aluminium sheeting.

**PRODUCT BENEFITS:**

Hard dry within 4 hours enabling 2 coats to be applied the same day. Easy application with brush, roller or airless spray. An appealing sheen finish. Easy clean up with water.

**SURFACE PREPARATION:****New Work:**

**GALVANISED IRON:** Remove fabricators pre-treatment with Galvanised Iron Cleaner and prime with WB Galvanised Iron Primer.

**CEMENT:** Surfaces should be free from dirt, friable material and foreign contamination. Apply first coat Trade Roof Paint diluted up to 20% with water followed by 2 more coats undiluted.

**Previously Painted Surfaces:**

Surface must be in a sound condition. Roof surfaces showing signs of flaking must be stripped. All chalky and powdery surfaces to be thoroughly sanded and hosed down. Surfaces with algae, lichen, moss etc must be cleaned using a high pressure water spray or by wetting the roof with clean water and applying a copper sulphate and water mixture, followed by scrubbing.

**PRECAUTIONS:**

Do not apply during cold, wet conditions.

Do not apply when roof is extremely hot (@noon on a hot day)

Do not apply directly to galvanised roofs unless dry, clean and primed.

Allow sufficient time for paint to dry before evening dew begins to settle.

Take care when using chemical treatments as they kill plant growth.

Avoid splashing and wear protective clothing and gloves. Do not apply to friable surfaces regardless of whether new, old or previously painted.

**Not suitable for roofs that act as catchments for drinking water.**

**APPLICATION:**

Ready for use by brush, roller or airless spray. Thinning is not normally necessary, unless surface is very porous, thin up to 20% clean water if required. Clean up with water.

**TECHNICAL DATA:**

Type:	Pure Acrylic
SG:	1.23 - 1.26
Drying Time: (T) @ 25°C (H):	1/2 - 1 hour 4 hours
Recoat:	2 hours
Finish:	Sheen
Viscosity:	85 - 95 KU
Solids Volume:	32 - 36%
Solids Mass:	42 - 46%
Spread Rate:	Approx. 8m <sup>2</sup> /Lt depending on surface profile and porosity.
Flashpoint:	Non-flammable
Colour Range:	Black, Terracotta, Charcoal, Brown, Platinum, Leaf, Steel, Green, Red Oxide
Pack Size:	5L & 20L
Recommended DFT:	50 - 75 micron

**Health and Safety:**

Refer to Material Safety Data Sheet